

----- = RAMESH EPR PELLETS RE-DO 2NDHT (EPRAPELH2)

030030

HEAT FLOW (mW)

3.75

2.5


1.25

0

Peak from: 120.56  
to: 156.62  
Onset = 130.60  
J/g = 22.45

Ethylene-Propylene Rubber

Peak = 139.27



Date: Date not entered

Scanning Rate: 10.0 C/min

Sample Wt: 3.100 mg Path: C: \PE\

File 1: EPRAPELH2 G.N.M.

PERKIN-ELMER DSC7

2

30030

